

## Product Information Finishing Auxiliaries

### Evo<sup>®</sup> Soft ANI

**Function** Liquid softener for all natural and synthetic fibres

- Properties**
- Full, soft, flowing handle
  - Suitable for use in resin finishing liquors
  - Suitable for exhaust, pad and spray application
  - Does not impair whiteness at temperatures up to 170°C
  - Does not counteract the fluorescence of optically brightened goods
  - Stable to normal-use concentrations of acids and alkalis
  - Stable in hard water

**Chemical Characteristics** Fatty acid condensation product

**Technical Data**

Form supplied: cream-coloured, pourable product

pH: 6,5 – 8,5

Ionicity: nonionic

Density at 20 °C: approx. 1.0 kg/l

Dilution procedure: can be diluted in any ratio with water at room temperature

Shelf life: 6 months in original closed containers.

**Useless after frost effect**

**Do not store product below + 3°C and above +35°C!**

## Application

---

### Pad Application

*To modify handle:*

1 g/l acetic acid 60%

5 - 30 g/l Evo Soft ANI

*Raising and emerizing additive for cotton:*

1 g/l acetic acid 60%

40 g/l Evo Soft ANI

1 g/l Sera Wet M-DF

### Exhaust Application

*Handle-modifying additive for application in drum washing units:*

For garments and denim articles, especially white goods

Add to last rinse bath:

1 – 5 g/l Evo Soft ANI

pH: 4.5 - 5 (acetic acid)

Treatment time: 5 - 15 min

Temperature: 25 - 40°C

Spin and tumble-dry

*Raising and emerizing additive for cotton:*

Winch beck or jig

3 - 4 g/l Evo Soft ANI

0.5 g/l Sera Wet M-DF

Liquor pH: 4.5 - 5

Treat for 30 - 40°C / 10 - 20 min

Dry at 110 - 140°C

---

**DyStar Kimya Sanayi ve Ticaret Ltd. Şti**  
**Mecidiye Mah.Cenap Şahabettin Sok.No:24**  
**34718, Koşuyolu / Kadıköy – İstanbul**

Telefon 0 216 544 15 00

Faks (satış) 0 216 339 90 48

Faks (pazarlama) 0 216 339 90 63

[DyStar.Auxiliaries@DyStar.com](mailto:DyStar.Auxiliaries@DyStar.com)

[www.DyStar.com](http://www.DyStar.com)

This information and our technical advice - whether verbal, in writing or by way of trials - are given in good faith but without warranty, and this also applies where proprietary rights of third parties are involved. Our advice does not release you from the obligation to check its validity and to test our products as to their suitability for the intended processes and uses. The application, use and processing of our products and the products manufactured by you on the basis of our technical advice are beyond our control and, therefore, entirely your own responsibility. Our products are sold in accordance with our General Conditions of Sale and Delivery.