

Product Information Laundry Auxiliaries

Lava[®] Cell BNG Conc

Function Cellulase enzyme for biopolishing and permanent antipilling effect, improvement in the handle of fabrics made of cellulosic fibers, suitable for defibrillation of Lyocell fibers.

- Properties**
- decreases fuzz and pilling of cellulosic fibers
 - durable softness, smoothness without loss of water absorbency
 - removes fiber fibrils from Lyocell after fibrillation treatment
 - gives a soft, elegant handle
 - improvement of color brightness and intensity
 - favorable ecological profile finish

Chemical Characteristics Highly concentrated enzyme preparation on cellulase basis

Technical Data

Appearance:	yellow to redbrown liquid
Dilution procedure:	dilute with warm and cold water dissolve in cold water
pH:	4 – 6
Shelf life:	12 months in closed original containers

Do not store product above +25°C, product can become useless.

Store product cool but not below +3°C

Application

Lava Cell BNG Conc is a special enzyme which acts on the surface of cellulosic fibers. It weakens the micro fibrils on the surface of the fiber and gives fabrics a softer, more elegant handle. The effect is permanent and reduces hairiness and pilling of many fabrics.

Treatment can be performed at any stage but the best results are obtained after desizing, bleaching, washing or dyeing.

The product should be applied on units with strong mechanical action such as jets, overflow dyeing machines or drum washing machines. Alternatively, mechanical treatment can be performed after treatment with Lava Cell BNG Conc in a tumble drier.

Typical recipe:

0.2 – 0,8	%	o.w.g. Lava Cell BNG Conc
0.5	%	sodium acetate
0.5	%	acetic acid 60%

A pH of 4.5 - 5 is normally set automatically. If necessary, it can be adjusted with acetic acid.

Liquor ratio 5:1 to 10:1, depending on type of machine
Treatment time: 10 - 45 min / 55 - 60°C

Enzyme activity should be stopped after treatment by adding alkali (soda or caustic soda) to set the pH at above 9 or by alkaline post scouring over pH 9 or by setting the temperature over 75-80°C.

The other dyeing, bleaching and finishing treatments are not influenced by treatment with Lava Cell BNG Conc. The handle can be improved by applying common softeners, especially silicone softeners.

Treating cellulosic fibers with Lava Cell BNG Conc. reduces tensile strength. If the weight loss is 3 - 5%, the reduction in tensile strength is usually 10 - 20%. Particular attention must be paid to the reduction in tensile strength when treating bast fibers. Pre-trials should always be carried out to check tensile strength before treating new fabrics.

DyStar Kimya Sanayi ve Ticaret Ltd. Sti
Mecidiye Mah.Cenap Sahabettin Sok.No:24
34718, Kosuyolu / Kadikoy
Istanbul - Turkey
Telephone +90 216 544 15 00
Fax(sales) +90 216 339 90 48
Fax (marketing) +90 216 339 90 63
DyStar.Auxiliaries@DyStar.com
www.DyStar.com

This information and our technical advice - whether verbal, in writing or by way of trials - are given in good faith but without warranty, and this also applies where proprietary rights of third parties are involved. Our advice does not release you from the obligation to check its validity and to test our products as to their suitability for the intended processes and uses. The application, use and processing of our products and the products manufactured by you on the basis of our technical advice are beyond our control and, therefore, entirely your own responsibility. Our products are sold in accordance with our General Conditions of Sale and Delivery.