

Product Information Laundry Auxiliaries

Lava[®] Fin FRC

Function Special coating finish for all fabrics

- Properties**
- provides shine effect on direct application
 - product can be diluted with water
 - special coating resin, covering type and self-polishing, for which the main feature is the tendency to OXIDIZE by friction
 - there is no need high temperature for shine effect
 - no need pressing after application to get nice glossy leather looking effect
 - ready to use product
 - the visual effect obtained is irreversible

Chemical Characteristics Polymer dispersion combined with different fillers

Technical Data

Appearance:	gray colored viscous dispersion
pH:	7,5 – 8,5
Dilution:	can be diluted in any portion with water at room temperature
Shelf life:	12 months in original closed containers

Stir well before sampling or use

Application

Lava Fin FRC is a ready to use compound to obtaining suitable leather effects without press. The main future is the tendency to OXIDIZE by friction. Coating color will be changed as **Black** by friction and this **Black** color is very visible on light tones while on dark tones not so much and this Black color will be permanent on the garment after friction.

Spray application

For shiny coating on fabric, spray following solution

Lava Fin FRC - 30-60 %

Lava Protect XL - 3-5 %

Water - 35-65 %

Pigment dyestuff – x %

Sprayed amount is determined depending on the fabric and the final desired effect, and depending on this different additives may be used.

Finally spread the product on the fabric with a soft dry brush.

Drying at room temperature 15-20 minutes

Rubbing by hand with fabric or sponge on the areas which is required to be seen black color

Cure at 150°C for 10-20 min.

Lava Fin FRC is providing wet washing resistance at 40°C with detergent and has good rubbing fastness. The visual effect obtained is irreversible. With the continued use of the garment, Black color effect will become increasingly evident. The garment appearance changes over time while wearing it.

DyStar Kimya Sanayi ve Ticaret Ltd. Sti
Mecidiye Mah.Cenap Sahabettin Sok.No:24
34718, Kosuyolu / Kadikoy

Istanbul - Turkey

Telephone +90 216 544 15 00

Fax(sales) +90 216 339 90 48

Fax (marketing) +90 216 339 90 63

DyStar.Auxiliaries@DyStar.com

www.DyStar.com

This information and our technical advice - whether verbal, in writing or by way of trials - are given in good faith but without warranty, and this also applies where proprietary rights of third parties are involved. Our advice does not release you from the obligation to check its validity and to test our products as to their suitability for the intended processes and uses. The application, use and processing of our products and the products manufactured by you on the basis of our technical advice are beyond our control and, therefore, entirely your own responsibility. Our products are sold in accordance with our General Conditions of Sale and Delivery.